

QC-116/QC-116A Digital Mullen Burst Tester

Standard

ISO-2759, GB/T 6545, JIS-P8112, JIS-L1018, ASTM D3786, TAPPI-T403, TAPPI-T810, TAPPI-T807

Description

The Mullen Burst Tester is used for samples such as base paper, corrugating paper, leather, synthetic leather. This tester is a digital type that features automatic compensation mechanism and sensor calibration to obtain a more accurate test result. The real-time force graph shows current status in various units for user's choice, facilitating user's data reading.

Industry


Paper, Textile, Leather





Specification

Туре		QC-116 (High pressure)	QC-116 (Low pressure)	Textile
Test speed		170 ± 15 ml/min	95 ± 5 ml/min	98 ± 4 ml/min
Pressure display		D1 Control touch panel		
Capacity (kg/cm ²)		75kg/cm ²		
Platen diameter	Upper	31.5 ± 0.05mm	30.5 ± 0.05mm	30.5 ± 0.05mm
	Lower		33.1 ± 0.05mm	30.5 ± 0.05mm
Gear position		Pressurization, neutral, return		
Dimension		53 × 33 × 58 cm		
Weight around		60 kg		
Power		Single phase 110~240VAC, 5A		

Standard accessories - display







- Metric/imperial unit.
- Graph: real-time pressure and bursting time.
- Compensation mechanism: automatic compensation in reference to aluminum foil.
- Equipped with a 7-inch touch screen.
- Pressure gauge: powered by a smart, precise electric sensor.
- Up to 50 test data can be saved.
- Data exportable to USB.
- Chinese, English and Japanese available.

Rubber diaphragm and aluminum foil



Low pressure Pressure:0~10 kgf/cm²



High pressure Pressure:10~75 kgf/cm²



Standard foil For calibration

*Cometech reserves ultimate modification right of product specification.



COMETECH TESTING MACHINES CO,LTD.

No.49,Ln,39,Lianucn Rd, Fengyuan Dist, Taichung City420,Taiwan

Tel:886-4-25368881 / Fax:886-4-25368883

E-mail: sales@come-tech.com.tw
URL: http://www.come-tech.com.tw

